

## Fenomastic Wonderwall Silk

**Surface:** Cement Plaster/Block Work/Concrete/Gypsum Board/Gypsum Plaster/Other rendered surfaces

### Primer Coat

One coat: Jotun Fenomastic Emulsion Primer:

Vol. solids: 25±2 %

### Filler Coat

Two coats: Jotun Stucco:

Vol. solids: 50% ±2 %

### Topcoats

Two coats: Jotun Fenomastic Wonderwall

Vol. solids: 38±2 %

### Properties

- **VOC content**  
1.36 g/l (US EPA 24)
- **Washability/Scrub Resistance**  
More than 25000 scrubs-DIN 53778  
Film thickness reduction after 200 cycles: 2.03 microns-EN ISO 11998
- **Hazardous Materials**  
  
Free from:
  - Heavy Metals (ASTM D 3338)
  - APEO (US EPA 8260)
  - Formaldehyde (US EPA 8260)
- **Burnish Resistance**  
Gloss change after subjecting to burnish test:  
60° = 1.1 units  
85° = 1.5 units
- **Polish Resistance**  
Gloss change after subjecting to polish test:  
60° = 0.1 units  
85° = 2.1 units
- **Stain Penetration**  
Rating = 0, No penetration observed (0=Best & 2=Worst)
- **Easy Clean**  
Rating: 0-1, 2 only for crayon (ASTM D 4828:94) (0=All stains removed & 2=No stains removed)
- **Hiding Power**  
97.28-ASTM D 2805
- **Colour Rub-off**  
Rating: Class A (Class A: Very high resistance to colour rub-off  
Class E: Low resistance to colour rub-off)
- **Resistance to household chemicals**  
Resistant-ASTM D 1308