

Jotafloor Rapid Dry WB

Surface: Concrete floor

Preparation: Dust Free Captive Blasting, diamond disc grinding (other methods may be considered on case by case basis)

Recommended Use: Exhibition Hall, In-house events, Concerts/Sports venues, Open days (For light duty general purpose use and where drying time is at a premium)

Initial Coat

One coat: Jotafloor Rapid Dry WB: (25 microns)

Vol. solids: 56±2 %

Traction Layer (Optional)

Anti-Skid Powder (Aluminium Oxide grains)

Topcoat

Two coat: Jotafloor Rapid Dry WB (25-50 microns)

Vol. solids: 36±2%