

## Jotafloor Tex

**Surface:** Power floated concrete floor

**Preparation:** Dust Free Captive Blasting (other methods may be considered on case by case basis)

**Recommended Use:** Designed for a wide range of floors with various levels of mechanical and chemical exposure. Recommended for car parks, warehouses, garages, dairies, factories, laboratories, aircraft hangars, food, beverage and plant rooms.

### Primer Coat

One coat: Jotafloor Solvent Free Primer: (100-150 microns)\*

Vol. solids: 98±2 %

### Traction Layer (Optional)

### Topcoats

One/Two coats: Jotafloor Tex (300 microns)

Vol. solids: 98±2 %

### Properties

- **Impact Resistance**  
No sign of cracks or disbonding (ASTM D 2794)
- **Pull off adhesion**  
2.4 MPa (ASTM D4541) Failure within the substrate.
- **Shore "D" Hardness**  
55 (ASTM D2240)
- **Shore "A" Hardness**  
85 (ASTM D2240)
- **Taber Abrasion**  
180 mg after 1000 cycles/CS-17 wheel (ASTM D4060)

\*Different primer may be considered on case to case bases.