

## Jotafloor Topcoat E

**Surface:** Concrete floor

**Preparation:** Dust Free Captive Blasting, diamond disc grinding (other methods may be considered on case by case basis)

**Recommended Use:** Warehouses, Garages, Workshops, Production areas,

### Primer Coat

One coat: Jotafloor Solvent Free Primer: (100-150 microns)\*

Vol. solids: 98±2 %

### Traction Layer (Optional)

Broadcast Jotafloor Non-Slip aggregates

### Topcoats

One/Two coats: Jotafloor Topcoat E (125-300 microns)

Vol. solids: 98±2 %

### Properties

- **Compressive Strength**  
103 N/mm<sup>2</sup> (ASTM C579)
- **Tensile Strength**  
9 N/mm<sup>2</sup> (ASTM C307)
- **Shore "A" Hardness**  
92 (ASTM D2240)
- **Taber Abrasion**  
66 mg after 1000 cycles/CS-17 wheel (ASTM D4060)
- **Crack bridging ability**  
1.62 mm (ASTM C836)
- **Resistance to Mold growth**  
No Mold growth after 4 weeks (Scale 10 as per ASTM D3273)

\*Different primer may be considered on case to case bases.