

Jotashield Decor Traditional Tex

Substrate: Plaster/CMU/Concrete

Primer Coat

One coat: Jotashield Penetrating Primer or Jotashield Water Based Penetrating Primer:

Vol. solids: 37±2 %

Texture coats

Two coats: Jotashield Decor Traditional Tex

Vol. solids: 52±2 %

Properties

- **VOC content**
0.1 g/l (EPA Method 24)
- **Determination of Carbon Dioxide**
Equivalent Air Layer Thickness: 233m
Equivalent of 400mm concrete: 58cm
- **Determination of Moisture Resistance**
Equivalent Air Layer Thickness: 0.3m (avg)
- **Crack bridging ability**
Up to 0.6 mm

Glaze Coat (Optional for a two tone effect)

One coat: Jotashield Decor Glaze

Vol. Solids: 34±2 %

- Properties are for the top coat only tested with Jotashield Penetrating Primer unless otherwise mentioned.
- When more than one result is presented one star* identifies the product being tested with Jotashield Alkali Resistant Primer and two stars** identify that the product is tested with Jotashield Penetrating primer.