

# Lady Design Stucco Antica

**Surface:** Plaster/CMU/Concrete/Gypsum Board Partition

## Primer Coat

One coat: Jotun Fenomastic Emulsion Primer:

Vol. solids: 25±2 %

## Filler Coat

Two coats: Jotun Stucco:

Vol. solids: 50% ±2 %

## Topcoats

Two coats: Jotun Fenomastic My Home Rich Matt

Vol. solids: 40±2 %

## Properties

- **VOC content**  
23.9 g/l (US EPA 24)
- **Washability/Scrub Resistance**  
>10,000 scrubs (DIN 53778)
- **Hazardous Materials**  
Free from:
  - Heavy Metals (ICP-AES)
  - APEO (BS 3762:90)
  - Formaldehyde (UV Spectroscopy)
  - Phthalates (GCMS)
- **Burnish Resistance**  
Gloss Change:  
60° = 0.1 units  
85° = 0.9 units
- **Polish Resistance**  
Gloss change:  
@ 60 = 0.4 units  
@ 85 = 6.9 units
- **Contrast Ratio/whiteness**  
97.00/94.82 (ASTM D2805-88)
- **Practical Washability:**  
Rating 0-2: (ASTM D4828:94)
- **Colour rub off:**  
Class A

(0 = All stains removed & 2 = No stains removed)

(Class A = Best & Class E = Worst)

**Top coats:**

Four coats Lady Stucco Antica

Vol. solids: 50±2 %,

VOC: 5 g/l (ISO 11890 EU)